

Arsenic and Lead Removal from Water by Nano-photocatalytic Systems (A Review)

Shaghayegh Sadr¹, Amir Ershad Langroudi^{*2}, Arezoo Nejaei³, Ahmad Rabiee⁴, Nabiollah Mansouri⁵

1. Department of the Environmental Science, Faculty of Natural Resources and Environment, Science and Research Branch, Islamic Azad University, Tehran, Iran.
2. Department of Color, Resin and Surface Coatings, Faculty of Processing, Iran Polymer and Petrochemical Institute (IPPI), Tehran, Iran.
3. Department of Environment, Faculty of Agriculture and Natural Resources, Tabriz Branch, Islamic Azad University, Tabriz, Iran.
4. Department of Polymer Science, Iran Polymer and Petrochemical Institute (IPPI), Tehran, Iran.
5. Department of Environmental Engineering, Faculty of Natural Resources and Environment, Science and Research Branch, Islamic Azad University, Tehran, Iran.

*Correspondence author: a.ershad@ippi.ac.ir

Received: 20 January 2021/ **Accepted:** 23 February 2021/ **Published:** 30 February, 2021

Abstract: Water is an essential component in the world. The presence of heavy metals in water has dramatic effects on health and ecological process in the environment. Heavy metal pollution in water bodies is an existing and developing problem in the world. There are several methods for removing these pollutions in water. A photocatalytic degradation is a useful approach to removal a variety of heavy metals from contaminated water. In this study, we summarized different types of methods for the removal of heavy metals especially arsenic and lead from water. Studies include different nano-photocatalyst and methods such as the use of TiO₂ substrates, TiO₂ nanotubes, and nanocrystals, organic and inorganic nanoparticles based on silica, a variety of nanomaterial-based polymers, magnetic nanoparticles such as zero-valent iron and zinc oxide, or using two or more of these nanomaterials at the same time as an adsorbent or oxidizer of pollutants, all under visible or ultraviolet light. Each method has some limitations and advantages and based on different research that scientists presented, the efficiency of each technique is dependent on some conditions such as pH, adsorption time, solvent type, and UV light, so we still can't introduce the best method. Nowadays researchers are trying to find a method with high efficiency, low cost, least risk for the environment, and without secondary contamination. Hopefully, researchers find many promising methods that can be used with high efficiency in the future by continuing the research.

Keywords: Adsorption, heavy metals, photocatalytic, pollution, water.



This work is licensed under a Creative Commons Attribution-Non Commercial 4.0 International License. To read the copy of this license please visit: <https://creativecommons.org/licenses/by-nc/4.0>

1. Introduction

Water is one of the most important sources that uses in industries, agriculture, urban uses etc. Water quality is fundamental for the health of people and sustains ecological processes that support native populations of fish, vegetation, wetlands, and bird lives (Mirzaei et al., 2016; Fataei et al.,). Although implementing rigorous standards on metal emission and recycling them from wastewater and water are effective for controlling these pollutants. (Zhou Q. et al., 2020), increasing the population of the world and supplying sanitary water has become one of the fundamental

problems of today's world, and the development of industries and the production of sewage with toxic and complex compounds, has limited the use of conventional processes of wastewater treatment. Heavy metals are metals with relatively high densities that some of them are essential nutrients and some of them are highly poisonous and toxin. Many heavy metals originate yearly from anthropic activities (Smail et al., 2012) and their toxicity has become the focus of many institutions, industries, and environmental groups (Alka S. et al., 2020). The release of heavy metals into the environment due to their toxicity and stability increases the risks to health and the environment. Metals from industrial

wastes, agricultural sources, urban runoff, and automobile emissions could also disperse to the surface water via surface runoff or rainwater (Smail et al., 2012).

They could move to soil layers, and eventually reach groundwater (Bichet et al., 2013).

Exposure to heavy metals can cause various diseases such as mental retardation, nerve disorders, memory, and behavioral problems, etc. Some heavy metals were used for industrial purposes and the most important threat of these activities is related to groundwater pollution that is used as a source of drinking water, so the health of people in the world is threatened with the use of these waters (Andjelkovic et al., 2015). For this reason and since these pollutants are badly affecting the aquatic habitats and are flexible to the food chain. (Pandiyani et al., 2020) it is essential to remove them from the environment (Chowdhury et al., 2016). Contamination of drinking water with heavy metals could be poisonous and is carcinogenic to humans (Rengaraj et al., 2007) as they are considered as eminent toxicants which hence to adverse health impacts (Kapoor & Singh, 2021)

There are many techniques that can be used to remove heavy metals from waters like coagulation–flocculation and electrocoagulation, physical and biological adsorption, ion exchange, membrane separation and photocatalytic reduction (Majidnia & Idris, 2015). In this article we discuss about the photocatalytic system.

An efficient and effective method for the removal of heavy metal ions in polluted water is photocatalysis of semi-conductor oxides via oxidative and reductive mechanisms (Nouri Dodaran et al., 2019; Prabhu et al., 2014). Photocatalytic activities are a series of advanced Oxidation technologies to alleviate the problems of water pollution and these activities are effective for treating contaminants in water systems. For this purpose, there are many catalysts for example ZnO, ZnS, perovskites, MoS₂, TiO₂, WO₃, and so on (Byrne et al., 2017).

In order to achieve mentioned objectives, this article aims to review new studied methods based on nanophotocatalysts to remove two toxic and harmful heavy metals (arsenic and lead).

2. Literature reviews

There has been an extensive number of studies about photocatalysis and different catalysts for using that. In this article, we mention some of them.

2.1. Using titania polyvinyl alcohol–alginate beads

Majidnia and Fulazzaky (2016) checked out removal of lead cations (Pb²⁺) from aqueous solution by Titania polyvinyl alcohol–alginate beads. In this method magnetic nanoparticles were prepared by combining ferrous and ferric chloride in the presence of ammonium

hydroxide by alkaline co-precipitation and thus the precipitation of magnetite (Fe₃O₄) appeared to be as black-colored precipitates.

They performed the tests of photoreduction of Pb²⁺ cations by both Titania polyvinyl alcohol–alginate beads (TPVAABs) and maghemite polyvinyl alcohol–alginate beads (MPVAABs) in batch experiments. The results showed that the use of MPVAABs is more effective than TPVAABs after 135 min of reaction time under sunlight irradiation to remove Pb²⁺ cations. They stated use of Titania polyvinyl alcohol–alginate beads are a rapid and reliable method for treating heavy metal-contaminated in the water.

2.2. Using Nanomaterials

Nanomaterials are materials that have the particle size between 1 nm to 100 nm and they are useful tools for removal of heavy metal, because they have unique structure and surface characteristics (Wang et al., 2012).

Lu and Astruc (2018) summarized the application of nanomaterials for the removal of heavy metals in water. We mention them below.

2.2.1. Inorganic nanomaterials

Inorganic nanomaterials are including transition metal oxide, carbon-based nanotube and Si-based nanomaterials.

2.2.1.1. Transition metal oxide

Metal oxides can be used to remove heavy metals from water bodies such as titanium oxide, magnesium oxide, copper oxide, iron, etc. Iron oxide nanomaterials and Fe₃O₄ nanomaterials have used widely to remove heavy metals in water for example polystyrene supported-hydrated hematite (Fe₂O₃) can adsorb arsenic (As³⁺ and As⁵⁺) (Cumbal and Sengupta, 2005). Also, nano-Fe₃O₄-silica (SiO₂) can remove heavy metals copper (Cu²⁺) and Pb²⁺ cations from water.

2.2.1.2. Carbon-based nanotube

Carbon based nanomaterials are one of the most important method to remove heavy metals in the world (Lu and Astruc, 2018). Research studies show that carbon black based nanotube can adsorb Cu²⁺, Zn²⁺, palladium (Pd²⁺) and cadmium (Cd²⁺) cations (Wang et al., 2009; Chen et al., 2010; Zhou et al., 2010).

2.2.1.3. Silica -based nanomaterials/ Titanate nanotubes

It has been reported that nanoporous silica, silica nanofibers, Si nanotubes, and Si-coated magnetic nanoparticles can remove heavy metals from water ecosystems (Yantasee et al., 2010). In this category, the introduction of molecules bearing sulfhydryl (-SH) groups onto the surface of silica nanofibers can remove mercury (Hg²⁺) cations from water with high efficiency.

Nie and Teh (2010) used titanate nanotubes as superior adsorbents for removal of Pb^{2+} cations from water. In their study, TiO_2 nanopowder was mixed with sodium hydroxide (NaOH) solution and was moved to autoclave at $140^\circ C$ for 48 h and then cooled down to room temperature. Then, the precipitate was separated and washed with deionized water a few times until the pH value reached to about 7, followed by twice of alcohol (ethanol) washing. Finally, the sample was dried in air at $80^\circ C$ for 24. Adsorption experiments were done using the batch equilibration method. For that, titanate nanotubes were added into lead nitrate ($Pb(NO_3)_2$) solution. Then the mixture was shaken in a thermostatic shaker for 48h. Afterward, precipitates were separated by centrifugation and concentration of Pb^{2+} was analyzed by plasma-atomic emission spectrometer. The crystal structure of the products was investigated by X-ray diffraction (XRD) analysis. In their research Adsorption capacity was calculated by following equation:

$$K_d = \frac{(C_0 - C_f) V}{C_f M}$$

Formula of distribution coefficient (Yantasee et al., 2010)

Where C_0 and C_f are the initial and the final concentration of target species, affinity was quantitated via calculation of distribution coefficient (K_d , mL/g; eq 1), V is the matrix volume, and M is the mass of the sorbent. Energy-dispersive X-ray (EDX) analysis indicated that the chemical composition of the initial nanotubes is $Na_2Ti_4O_9$ and the sodium cations in the titanate nanotubes can be fully replaced by Pb^{2+} cations. At the result, titanate nanotubes allow Pb^{2+} cations enter into nanotubes and the adsorption capacity will increase. Also, the crystal structure of titanate nanotubes can recover after the adsorption cycle, so this technique is an effective method for economic treatment.

2.2.2. Organic nanomaterials

Organic nanomaterials bearing amine ($-NH_2$), hydroxyl ($-OH$), carboxyl ($-COOH$), etc. in the surface adsorb heavy metals in water. Metal-organic framework-derived nanomaterials (MOFs), for remediation are highlighted. The application of MOFs for wastewater treatment (adsorption and catalytic degradation) has been emphasized (He et al., 2020).

2.2.2.1 Organic Polymer nanomaterials

It has been reported cellulose nanocrystals, cellulose nanofibers and chitin nanocrystals can remove Silver cations (Ag^+) ions from contaminated water (Liu et al., 2014). Also, nanocellulose fibers with vinyl sulfonic acid help to remove chromium (Cr^{3+}), nickel (Ni^{2+}), Cd^{2+} and Pb^{2+} cations (Kardam et al., 2012).

2.2.2.2. Organic Polymer supported nanomaterials

Amine groups can play significant roles in modified chitosan for the adsorption of heavy metal ions. New recyclable chitosan modified adsorbents (GMCS) for adsorption of Lead cations (Pb^{2+}) is one of these inventions (Ge and Du, 2020)

Synthetic organic polymer-supported nanomaterials (polyaniline (PAN), polystyrene, polyhydroxybutyrate (PHB), poly (tetrafluoroethylene), polyethylene (PE), and nafion) and biopolymer-supported nanomaterials (cellulose, chitosan, and alginate or resin) are important organic materials to remove heavy metals. For example, tetraethylenepentamine-functionalized magnetic cellulose composite removes Hg^{2+} , copper (Cu^{2+}) and Ag^+ cations (Klemm et al., 2011).

2.3. Preparation Titania–silica (TiO_2 – SiO_2) photocatalyst by modified sol–gel technique

Harraz et al (2013) investigated on TiO_2 – SiO_2 photocatalyst for cyanide (CN^-) degradation and heavy metals removal. A mixture of TiO_2 – SiO_2 can be operated as a good catalyst for removal toxic materials. In sol-gel technique the first, the combination of titanium tetrachloride solution ($TiCl_4$) with ammonia solution (NH_4OH) led to production a white precipitate at pH 7. Then precipitate was washed with deionized water to remove the excess Cl^- and NH_4^+ ions. Then a suspension was obtained. Afterward, nitric acid (HNO_3) was added to suspension and that was peptized to form a highly stable titania sol. Then tetraethyl orthosilicate (TEOS) solution was added into the above titania sol. In the next step, modified sol was dried and calcined at $400^\circ C$ for 3 h to obtain SiO_2 – TiO_2 catalyst. Finally, for heavy metals removal experiments, the wavelength of the used UV lamp is 365 nm and a specific weight of catalyst was suspended into the reactor with 300 ml of nitrate salts mixture (100 ppm of each metal ions: Cr (III), Co (II) and Pb (II)) and eventually removal percentage of heavy metals was calculated by inductive coupled plasma (ICP) analysis. The result shown that the efficiency if this technique is the best for Pb^{2+} . Also, Wang et al., 2017 researched mesoporous TiO_2/SiO_2 nanocomposites under photocatalytic oxidation can convert high-toxic As^{3+} to low-toxic As^{5+} . In their research, P123 and tetraethyl orthosilicate (TEOS) dissolved into ethanol under magnetic stirring for 0.5 h. Under stirring, Tetrabutyl titanate (TBOT) and concentrated hydrochloric acid were added to the above solution. After 0.5h the homogenous solution was transferred into a ceramic vessel and impounded for 18 h at room temperature in air to produce a rigid gel. The gel was covered with a layer of liquid paraffin 2–3 mm thick and heated at $60^\circ C$ for 18 h for removing ethanol. Then, the liquid paraffin was collected and cleared by filter paper and samples were calcined at $300^\circ C$ for 4 h and the products were refluxed with

ethylene diamine. Afterward, the obtained powders were washed by deionized water and dried at 60°C. Finally, the resulting samples were calcined. The prepared samples are characterized in detail by thermogravimetric-differential scanning calorimetry, X-ray diffraction, Raman, transmission electron microscopy and nitrogen (N₂) adsorption. The results show effective efficiency for photocatalytic oxidation and adsorption of arsenic.

2.4. WO₃/TiO₂ nanoparticles by modified sol-gel technique/ tungsten trioxide (WO₃)

Mirghani et al (2015) studied photocatalytic reduction of Pb²⁺ by WO₃/TiO₂ nanoparticles. In their research, tungsten-doped TiO₂ was composed by modified sol-gel. Tungsten was mixed with methanol and hydrochloric acid. Then sulfuric acid was added it and dried in an oven for 12 h at 75°C. Afterward, this compound was calcinated at 450°C for 4 h. finally, scanning electron microscope analysis was done. After UV light (254 nm) Pb²⁺ solution was prepared by dissolving lead nitrate in deionized water at pH 6. Changes in lead concentration was measured using atomic absorption spectrometer. Results show when the percentage of WO₃ in the TiO₂ sample increases, the amount of lead adsorption increases too. Kim et al., (2015) were studied Photocatalytic oxidation mechanism of arsenite on tungsten trioxide under visible light. Under visible light, three oxidant species can be generated: valence-band hole (h⁺), hydrogen peroxide (H₂O₂), and hydroxyl radical (·OH). Results show the oxidation of As³⁺ to As⁵⁺ was done by hole not by H₂O₂ and ·OH.

2.5. Nanocrystalline TiO₂ coatings/ anatase TiO₂/TiO₂

Little works have been reported on the exact mechanism of adsorption and the effect of insulator silica (SiO₂) on structural change and type of adsorption and its method alone cannot completely omit pollutants, therefore always the problem of secondary pollution remains (Esfandiari et al., 2020).

Yang and Zhang (2010) were used nanocrystallineTiO₂ coating under N₂ and quartz crystal microbalance (QCM) method for removing Pb²⁺ from wastewater. QCM is a useful technique for research of the photocatalytic reduction and oxidation of metal ions (Si et al., 2002). The results of QCM measurements shows that the reduction efficiency of Pb²⁺ depends on the organic additives. The reduction of Pb²⁺ is depends on increase of HCOOH concentration. Efficiency of this organic matter for removing Pb is two times higher in comparison with ethanol (C₂H₅OH).

Guan et al., (2012) have reviewed on application of TiO₂ in As removal from water. They stated the

adsorption of inorganic and organic arsenic onto TiO₂-based materials are relatively well established, but it needs to continue more researches about combination of TiO₂ with other materials. Base on their study, there are various TiO₂ that researchers used for arsenic removal, for example: Nanocrystalline TiO₂ particles, titanate nanotubes, hydrous TiO₂, granular TiO₂, TiO₂-impregnated chitosan beads and etc.

Li et al., (2014) were used anatase TiO₂ with high surface hydroxyl group density for removing As³⁺ from aqueous solution. Under UV light, anataseTiO₂ operates as both a photocatalyst and adsorbent and can adsorb arsenite with high efficiency. In their study, As³⁺ was oxidized by ·OH radicals on TiO₂ pillared montmorillonite in the presence of UV light. The results show UV light can increase the number of potential adsorption sites for As³⁺ on TiO₂. Mechanism of As³⁺ adsorption/oxidation on anataseTiO₂ with or without UV light is showed in figure 1 (Li et al., 2014).

Also, Li et al., (2012) studied TiO₂ pillared montmorillonite as a photoactive adsorbent for the removal of arsenic under UV irradiation. In their study, after the replacement of inactive sodium ions of montmorillonite with TiO₂, As can remove. The XRD analyses indicated that TiO₂/montmorillonite (MMT) contained Nanocrystalline titanium dioxide that these anatase TiO₂ nanoparticles were responsible for arsenic adsorption and photoactive adsorption. The results show that TiO₂/MMT can effectively remove arsenic from aqueous solutions under a wide range of experimental conditions, including pH, adsorption time and UV light.




Fig.1-Mechanism of As (III) adsorption/oxidation on anataseTiO₂ with or without UV light (Li et al., 2014).

Litter (2017) investigated the role of TiO₂-photocatalytic on removal of Cr, U and As. It is stated that there are three steps in this process: 1- direct reduction by photo generated electrons 2- indirect reduction by intermediates generated by hole or ·OH radical oxidation of electron donors (reducing radicals); 3- oxidative removal by holes or ·OH radicals. General

TiO₂ photocatalytic mechanism is represented in following:

- (1) $\text{TiO}_2 + h\nu \rightarrow e_{\text{CB}}^- + h_{\text{VB}}^+$
- (2) $e_{\text{CB}}^- + h_{\text{VB}}^+ \rightarrow \text{TiO}_2$
- (3) $e_{\text{CB}}^- + \text{A} \rightarrow \text{A}^-$
- (4) $h_{\text{VB}}^+ + \text{D}_{\text{ads}} \rightarrow \text{D}_{\text{ads}}^{++}$
- (5) $h_{\text{VB}}^+ + \text{HO}_{\text{surf}}/\text{H}_2\text{O}_{\text{ads}} \rightarrow \text{HO}^\bullet (+\text{H}^+)$
- (6) $\text{O}_{2\text{ads}} + e_{\text{CB}}^- (+\text{H}^+) \rightarrow \text{O}_2^{\bullet-} (\text{HO}_2^\bullet)$
- (7) $\text{O}_2^{\bullet-} + \text{H}_2\text{O} \rightarrow \text{HO}_2^\bullet + \text{OH}^-$
- (8) $2 \text{HO}_2^\bullet \rightarrow \text{O}_2 + \text{H}_2\text{O}_2$
- (9) $\text{H}_2\text{O}_2 + e_{\text{CB}}^- (\text{O}_2^{\bullet-}) \rightarrow \text{HO}^\bullet + \text{HO}^\bullet (+\text{O}_2)$

General TiO₂ photocatalytic mechanism (Litter, 2017)

Where:

e_{CB}^- = reductants

A = electron acceptors

D = donor species

h_{VB}^+ = oxidants

It has been concluded that this method is a valuable technology for removal of toxic metals and metalloids.

There are many other researches about impact of TiO₂ with different components on heavy metals (Torres and March, 1992; Murrini et al., 2008; Xu et al., 2007; Choi et al., 2010; Ferguson and Hering, 2006; Lee and Choi, 2002; Fostier et al., 2008; Yazdani et al., 2017).

2.6. Simultaneous photocatalytic oxidation and adsorption by TiO₂ and zero-valent iron

López-Muñoz et al., (2016) investigated impact of a combined system (TiO₂ + ZVI) under UV-irradiation on arsenic oxidation. The synergism impact of combination of TiO₂ and zero-valent iron shows high efficiency for removing As(III) and As(V) in their study and this reaction at pH=3 is more effective in comparison to pH=9.

2.6.1. Zero valent iron activated persulfate process

Hussain et al., (2017) used persulfate (PS) activated with zero valent iron (ZVI) for removal of As³⁺ from aqueous solutions. In their research, ferro cations (Fe²⁺) was used for activation of persulfate, because this metal is nontoxic, cost effective and environmentally friendly (Vicente et al., 2011). Also, ZVI is low cost, non-toxin, and with easy availability. The results show efficiency of As³⁺ oxidation is 96%.

2.7. Magnetic copper oxide CuO-Fe₃O₄ nanoparticles through photo oxidation and adsorption under light irradiation

Sun et al., (2017) was used CuO-Fe₃O₄ nanoparticles under light irradiation for As³⁺ removal. They demonstrated As³⁺ could be completely oxidized to

less toxic As⁵⁺ by CuO-Fe₃O₄ nanoparticles within 60 min in the photo-oxidation reaction and As⁵⁺ could be adsorbed onto the surface of nanoparticles. The results show with the excellent photocatalytic performance and high adsorption capability, this method has significant effect on As³⁺ removal. Figure 2 can demonstrate all reactions in this method (Sun et al., 2017).




Fig.2 -Photo-oxidation and adsorption mechanism of As³⁺ by CuO-Fe₃O₄, Sun et al., (2018)

Sun et al., (2018) studied the effect of magnetic CuO-Fe₃O₄ nanoparticles under visible light irradiation on degradation of p-arsanilic acid with arsenic. They concluded that magnetic CuO-Fe₃O₄ nanoparticles can convert p-arsanilic acid (p-ASA) to As⁵⁺ within 36 min completely and released As⁵⁺ could be adsorbed onto the surface of CuO-Fe₃O₄ nanoparticles with high efficiency above 95%.

2.8. UV/Peroxydisulfate (S₂O₈²⁻)

Yoon et al., 2011 studied on impact of UV/S₂O₈²⁻ on arsenic removal. The results shown UV/S₂O₈²⁻ is an effective oxidation process for arsenic removal.

2.9. Gadolinia-modified ceria photocatalyst

Ayawanna et al., (2015) used gadolinium oxide (Gd₂O₃-modified ceric oxide (CeO₂) particles to remove Pb²⁺ cations from aqueous solutions. They mixed Gd₂O₃ and CeO₂ powder in the 2-propanol for preparing Gd₂O₃-modified CeO₂ photocatalyst particles (Gd₂O₃-CeO₂). Then, the mixture was ground and dried for 4h. Afterward, the mixture calcinated and identified by an X-ray diffractometer. Pb²⁺ cations suspension liquid prepared by mixing Pb²⁺ cations solution and calcined Gd₂O₃-CeO₂. The suspension liquid is placed in an external irradiation-type quartz reactor and agitated for different duration. The results indicated a solid solution Gd_{0.1}Ce_{0.9}O_{1.95} phase coexisting with the CeO₂ matrix phase has more ability than two-phase mixture of Gd₂O₃-

CeO₂ to remove Pb²⁺ cations. When the UV irradiates the Gd_{0.1}Ce_{0.9}O_{1.95}-CeO₂, electrons in Gd_{0.1}Ce_{0.9}O_{1.95} generated and quickly transferred to the conduction band of CeO₂, and conversely the photo generated holes in CeO₂ quickly transferred to the valence band of Gd_{0.1}Ce_{0.9}O_{1.95} leading to an efficient separation between the photo generated electron-hole pairs in the Gd_{0.1}Ce_{0.9}O_{1.95}-CeO₂ photocatalyst.

2.10. Zirconium oxide (ZrO₂) and Zinc Oxide (ZnO) spheres

Cui et al (2013) studied on As (III, V) removal by ZrO₂ spheres. They demonstrated ZrO₂ spheres acts better than ZrO₂ nanoparticles for removal of arsenic. In their study, Zirconium oxychloride octahydrate (ZrOCl₂·8H₂O) was used as the raw material, deionized water as the solvent, aqueous ammonia (NH₃·H₂O) as the precipitation agent, and Agar powder (C₁₂H₁₈O₉)_n as the binding media. They used Freundlich model for defining adsorption capacity of ZrO₂ spheres (Deliyanni et al., 2007):

$$Q_{qe} = K_F C_{eq}^{1/n}$$

where Q_{eq} is equilibrium sorption capacity (mgPg⁻¹) of arsenic adsorbed, C_{eq} is the equilibrium phosphate concentration (mg/L⁻¹) in water samples, and K_F is the Freundlich constants (mg g⁻¹) (Lmg⁻¹)^{1/n}. They concluded that these ZrO₂ spheres acted a good adsorption capacity on both As³⁺ and As⁵⁺ at near neutral pH environment, without the need of pre-oxidation.

Because very limited studies were focused on the use of zinc oxide as an adsorbent for the removal of arsenic from aqueous solutions, a new adsorbent synthesized by gold nanoparticles (AuNPs) and zinc oxide (ZnO)-decorated zirconia (AuNPs/ZnO-ZrO₂) through coprecipitation and hydrolysis methods (Jiming Hua 2020) or by precipitation method, ZnO impregnated on agro-waste Biochars which were prepared by carbonization in mild condition, to improve adsorption capacity of arsenic (As⁵⁺) and lead (Pb²⁺) cations. (Cruz G.J.F. et al., 2020)

3. Conclusion

Water is an important element in life of people. Nowadays, water pollution with heavy metals has become a serious problem that is related to rapid urbanization, industrialization and agricultural area development. In most countries of the world, groundwater and surface water are at a serious risk of metal pollution. Severe effects of heavy metals have led to reduced growth and development, cancer, organ damage, nervous system damage, and in extreme cases, death. So, the effective removal of heavy metals from water sources is essential to ensure the health and life quality for millions of people that may be threatened by those. Many methods can be used to remove heavy

metals, but most of them are expensive and with scant efficiency. Thus, there is great need for the development of simple, low-cost, and highly efficient methods for the removal of heavy metals. Photocatalytic techniques are appropriate methods for removal of heavy metals. In this method, the electron holes created by the incident light can oxidize organic contaminants and the electrons released could be used to reduce metal ions in the water.

There are many photocatalytic techniques for removal of heavy metals from water bodies. Each of them has some advantages and limitations. All scientists are working to find the best solution for removal of these dangerous compounds from water. The meaning of the best method is finding a method with low cost and risk, high efficiency and with the least secondary contamination.

Advantage of inorganic nanomaterials is easy separation, but its limitation is secondary pollution possibility. Advantage of organic nanomaterials is high efficiency and limitation of organic nanomaterials is rather high cost. The benefits of adsorption process by Titania-silica photocatalyst is its simplicity, convenience, and high removal efficiency. Also, this method does not add any toxic pollutant, so health risk of this this process is very low, but performance of this method is not very high.

ZrO₂ spheres are non-toxic, highly stable, and resistant to acid and alkali, have a high arsenic adsorption capacity, and could be easily adapted for various arsenic removal apparatus.

Zero valent iron activated persulfate process is a good method because of its low cost and relatively high stability and solubility, but mechanism of the process remains as a controversial issue since no agreement has been reached over the true identity of the major oxidant species among superoxides, valence band holes, and ·OH radicals.

Titanate nanotubes is a good method for economic treatment because of recoverable structure.

In UV/TiO₂ method; As³⁺ is completely oxidized to As⁵⁺ by photo-oxidation. This method is a robust and low-cost approach without any damage of adsorbent, but the adsorption capacity of TiO₂ is very low, it causes inefficient removal of As⁵⁺.

The advantages of using TiO₂/MMT include its high efficiency for arsenic adsorption, faster adsorption rate, low equilibrium concentration of As³⁺ (0 µg L⁻¹) and As⁵⁺ (4 µg L⁻¹) with UV irradiation and low cost compared to the Nanocrystalline titanium dioxide.

In magnetic CuO-Fe₃O₄ nanoparticles method, there are high adsorption capacity of both CuO and Fe₃O₄, photoconductive and photochemical properties of CuO, so this method has high efficiency for removal of the heavy metals.

It can be concluded that all methods that are commonly used for heavy metals removal suffer from one or more drawbacks, limitations and scope of application and advantages of each method is depend on some conditions such as pH, adsorption time, solvent

type, heavy metal type and UV light, so we can't say that method is better than another.

4. Conflict of interest

The authors declare that they have no conflict of interest.

5. Additional Information and Declarations

Funding

I thank to Research and Development Unit, National Iranian Copper Industry Co., Sarcheshmeh-Kerman.

Grant Disclosures

Thanks to Iran Polymer and Petrochemical Institute (IPPI) and Science & Research Branch, Islamic Azad University of Tehran.

Competing Interests

The author declares there is no competing interests, regarding the publication of this manuscript

References

- Alka. S., Shahir SH., Ibrahim N., Ndejiko M.J., Vo, D.V.V., Manan F.A. (2020) Arsenic removal technologies and future trends: A mini review, *Journal of Cleaner Production*, Vol. 278, 123805.
- Andjelkovic, I. Stankovic, D. Jovic, M. Markovic, M. Krstic, J. Manojlovic, D. and Roglic, G. (2015). Microwave-hydrothermal synthesis of TiO₂ and zirconium doped TiO₂ adsorbents for removal of As (III) and As(V). *Journal of Saudi Chemical Society* 19, 429–435.
- Ayawannam, J. Teoh, W. Niratisairak, S and Sato, K. (2015). Gadolinia-modified ceria photocatalyst for removal of lead (II) ions from aqueous solutions. *Materials Science in Semiconductor Processing* 40, 136–139.
- Bichet C, Scheiffler R, Coeurdassier M, Julliard R, Sorci G, Loiseau C. (2013). Urbanization, trace metal pollution, and malaria prevalence in the House Sparrow. *PLoS One*, 8(1):e53866. <http://dx.doi.org/10.1371/journal.pone.0053866>.
- Byrne, C. Subramanian, G and Pillai, S. (2017). Recent Advances in Photocatalysis for Environmental Applications. *Environmental chemical engineering*: 1-60.
- Cumbal, L Sengupta, A.K. (2005). Arsenic removal using polymer-supported hydrated iron(III) oxide nanoparticles: role of donnan membrane Effect, *Environ. Sci. Technol.* 39, 6508–6515.
- Chowdhury, S. Mazumder, J. Al-Attas, O and Husain, T. (2016). Heavy metals in drinking water: Occurrences, implications, and future

In summary, more research needs to be done to find the best method with low treatment cost, at least operational complexity and high efficiency.

- needs in developing countries. *Science of the total environment*, 569, 476-488.
- Choi, W. Yeo, J. Ryu, J. Tachikawa, T. Majima, T. (2010). Photocatalytic oxidation mechanism of As(III) on TiO₂: unique role of As(III) as a charge recombinant species, *Environ. Sci. Technol.* 44, 9099–9104.
- Chen, J.H. Wang, Y.J. Zhou, D.M. Cui, Y.X. Wang, S.Q. Chen, Y.C. (2010). Adsorption and desorption of Cu(II), Zn(II), Pb(II), and Cd(II) on the soils amended with nanoscale hydroxyapatite, *Environ. Prog. Sustain. Energy* 29, 233–241.
- Cruz, G.J.F, Mondal D., Rimaycuna K., Gomez M.M., Solis J.L., Lang J. (2020) Agrowaste derived Biochars impregnated with ZnO for removal of arsenic and lead in water, *Journal of Environmental Chemical Engineering*, Vol 8, Issues 3, 103800.
- Cui, H. Su, Y. Li, Q. Gao, S.H. Shang, J.K. (2013). Exceptional arsenic (III,V) removal performance of highly porous, nanostructured ZrO₂ spheres for fixed bed reactors and the full-scale system modeling, *water research*, 47: 6258 -6268.
- Deliyanni, E.A., Peleka, E.N., Lazaridis, N.K., (2007). Comparative study of phosphates removal from aqueous solutions by nanocrystalline akaganeite and hybrid surfactant-akaganeite. *Separation and Purification Technology* 52 (3), 478-486.
- Esfandian N., Kahefi M., Mostafa M., Afsharnejhad S., Role of silica mid-layer in thermal and chemical stability of hierarchical Fe₃O₄-SiO₂-TiO₂ nanoparticles for improving of lead adsorption: Kinetics, thermodynamic and deep XPS investigation, *Materials Science and Engineering B*, Vol B. 262, 114690.
- Fataei E., Monavari SM., Hasani A/, Mirbagheri A., Karbasi A., (2011) Surface Water Quality Assessment Using Multivariate Statistical Techniques, *Environmental sciences*, 8 (4), 137-146.
- Ferguson, M.A. Hering, J.G. (2006). TiO₂-photocatalyzed As(III) oxidation in a fixed-bed, flow-through reactor, *Environ. Sci. Technol.* 40, 4261–4267.
- Fostier, A.N., Pereira, M.D.S.S., Rath, S. Guimaraes, J.R. (2008). Arsenic removal from water employing heterogeneous photocatalysis with TiO₂ immobilized in PET bottles. *Chemosphere* 72, 319–324.
- Ge, H., Juan D., (2020), Selective adsorption of Pb(II) and Hg(II) on melamine-grafted

- chitosan, *International Journal of Biological Macromolecules*, Vol. 162. 1880-1887.
- Guan, X. Du, J. Meng, X. Sun, Y. Sun, B. Hu, Q. (2012). Application of titanium dioxide in arsenic removal from water: A review. *Journal of Hazardous Materials*, 215–216: 1–16.
- Harraz, F.A. Abdel-Salam, O.E. Mostafa, A.A. Mohamed, R.M. and Hanafy, M. (2013). Rapid synthesis of titania–silica nanoparticles photocatalyst by a modified sol–gel method for cyanide degradation and heavy metals removal. *Journal of Alloys and Compounds* 551, 1–7.
- He, Y., Wang Z., Wang H., Zeng G., Xu P., Huang D., Chen M., Song B., Qin H., Zhao Y., (2020) Metal-organic framework-derived nanomaterials in environment related field: Fundamental, properties and applications, *Coordination Chemistry Reviews*, Vol 429, 213618.
- Hua Jinming (2020) Synthesis and characterization of gold nanoparticles (AuNPs) and ZnO decorated zirconia as a potential adsorbent for enhanced arsenic removal from aqueous solution, *Journal of Molecular Structure*, Vol 1228, 129842.
- Hussain, I. Li, M. Zhang, M. Huang, S.H. Hayat, W. Li, Y. Du, Y. and Liu, G. (2017). Efficient oxidation of arsenic in aqueous solution using zero valent iron activated persulfate process. *Journal of Environmental Chemical Engineering* 5, 3983–3990.
- Kapoor, Dh., Singh M.P. (2021) 10-Heavy metal contamination in water and its possible sources, *Heavy Metals in the Environment*, 179-189.
- Kardam, A. Raj, K.R. Arora, J.K. Srivastava, S. (2012). Artificial neural network modeling for biosorption of Pb(II) ions on nanocellulose fibers, *Bionanoscience* 2: 153–160.
- Kim, J. Moon, G.H. Kim, S. and Kim, J. (2015). Photocatalytic oxidation mechanism of arsenite on tungsten trioxide under visible light. *Journal of Photochemistry and Photobiology A: Chemistry* 311, 35–40.
- Klemm, D. Kramer, F. Moritz, S. Lindstrom, T. Ankerfors, M. Gray, D. Dorris, A. (2011). Nanocelluloses: a new family of nature-based materials, *Angew. Chem. Inter. Ed.* 50 (24), 5438–5466.
- Lee, H. Choi, W. (2002). Photocatalytic oxidation of arsenite in TiO₂ suspension: kinetics and mechanisms, *Environ. Sci. Technol.* 36, 3872–3878.
- Li, Y. Liu, J.R. Jia, S.Y. Guo, J.W. Zhuo, J. Na, P. (2012). TiO₂ pillared montmorillonite as a photoactive adsorbent of arsenic under UV irradiation. *Chemical Engineering Journal* 191, 66–74.
- Li, Y. Cai, X. Guo, J. Na, P. (2014). UV-induced photoactive adsorption mechanism of arsenite by anatase TiO₂ with high surface hydroxyl group density. *Colloids and Surfaces A: Physicochem. Eng. Aspects* 462, 202–210.
- Litter, M.I. (2017). Last advances on TiO₂-photocatalytic removal of chromium, uranium and arsenic. *Current Opinion in Green and Sustainable Chemistry*, 6:150–158
- Liu, P. Sehaqui, H. Tingaut, P. Wichser, A. Oksman, K. Mathew, A.P. (2014). Cellulose and chitin nanomaterials for capturing silver ions (Ag⁺) from water via surface adsorption, *Cellulose* 21, 449–461.
- Lu, F. Astruc, D. (2018). Nanomaterials for removal of toxic elements from water. *Coordination Chemistry Reviews* 356: 147–164.
- López-Muñoz, M.J. Arencibia, A. Segura, Y and Ruez, J.M. (2016). Removal of As(III) from aqueous solutions through simultaneous photocatalytic oxidation and adsorption by TiO₂ and zero-valent iron. *Catalysis Today*, 1-6.
- Majidnia, Z. Fulazzaky, M.A. (2016). Photoreduction of pb (II) ions from aqueous solution by titania polyvinylalcohol–alginate beads. 10, 44: 1-9.
- Majidnia Z, Idris A. (2015). Photocatalytic reduction of iodine in radioactive waste water using maghemite and titania nanoparticles in PVA-alginate beads. *J Taiwan Inst Chem Eng* 2015; 54:137–44.
- Mirghani M, Al-Mubaiyedh, U.A. Nasser, M.S. and Shawabkeh, R. (2015). Experimental study and modeling of photocatalytic reduction of Pb²⁺ by WO₃/TiO₂ nanoparticles. *Separation and Purification Technology* 141, 285–293.
- Mirzaei, M. Solgi, E. and Salmanmahiny, A. (2016). Evaluation of Surface Water Quality by NSFQI Index and Pollution Risk Assessment, Using WRATIC Index in (2015). *Arch Hyg Sci*, 5(4): 264-277.
- Murrini, L. Conde, F. Leyva, G and L. M.I. (2008). Photocatalytic reduction of Pb(II) over TiO₂: New insights on the effect of different electron donors. *Applied Catalysis B: Environmental* 84, 563–569.
- Nie, X.T. Teh, Y.L. (2010). Titanate nanotubes as superior adsorbents for removal of lead(II) ions from water. *Materials Chemistry and Physics* 123, 494–497.
- Nouri Dodaran, P., Fataei, E., Khanizadeh, B., (2019) Study on Photocatalytic and

- Sonocatalytic Activity of Bi₂O₃ Synthesized by Sol-gel Method in Removing Organic Compounds of Ardabil Textile Factory Effluents, *Journal of Water and Wastewater: Ab va Fazilab (in persian)* 30 (4), 67-77.
- Pandiyan, J., Mahboob Sh., Govindarajan M., Al-Ghanim, KH.A., Ahmed, Z., Mulh, N., Jagadheesan R., Krishnappa, K., (2020) An assessment of level of heavy metals pollution in the water, sediment and aquatic organisms: A perspective of tackling environmental threats for food security, *Saudi Journal of Biological Sciences*, Vol. 28, Issue 2, 1218-1225.
- Prabhu, S. Viswanathan, T. Jothivenkatachalam, K. Jeganathan, K. (2014). Visible Light Photocatalytic Activity of CeO₂-ZnO-TiO₂ Composites for the Degradation of Rhodamine B, *Indian Journal of Materials Science*: 1–10.
- Si, S.H. Huang, K.L. Wang, X.G. Huang, M.Z. Chen, H.F. (2002). Photocatalytic TiO₂ thin films by aerosol-deposition: From micron-sized particles to Nano-grained thin film at room temperature. *Thin Solid Films*, 422, 205.
- Smail EA, Webb EA, Franks RP, Bruland KW, Sanudo-Wilhelmy SA. (2012). Status of metal contamination in surface waters of the coastal ocean off Los Angeles, California since the implementation of the Clean Water Act. *Environ Sci Technol*, 46:4304–11.
- Sun, T. Zhao, Z.H. Liang, Z.H. Liu, J. Shi, W. and Cui, F. (2017). Efficient As(III) removal by magnetic CuO-Fe₃O₄ nanoparticles through photo-oxidation and adsorption under light irradiation. *Journal of Colloid and Interface Science*, 17, 1-35.
- Sun, T. Zhao, Z.H. Liang, Z.H. Liu, J. Shi, W. and Cui, F. (2018). Efficient degradation of p-arsanilic acid with arsenic adsorption by magnetic CuO-Fe₃O₄ nanoparticles under visible light irradiation. *Chemical Engineering Journal*, 334: 1527-1536.
- Torres, J. March, S. (1992). Kinetics of the photo assisted catalytic oxidation of Pb in TiO₂ suspensions. *Chemical engineering science*, 47 (15): 3857-3862.
- Vicente, F. Santos, A. Romero, A. Rodriguez, S. (2011). Kinetic study of diuron oxidation and mineralization by persulphate: effects of temperature, oxidant concentration and iron dosage method, *Chem. Eng. J.* 170 (1), 127–135.
- Wang, X. Guo, Y. Yang, L. Meihua, H. Zhao, J. and Cheng, X. (2012). Nanomaterials as Sorbents to Remove Heavy Metal Ions in Wastewater Treatment. *Journal of Environmental & Analytical Toxicology*. 2:154.
- Wang, Y.J. Chen, J.H. Cui, Y.X. Wang, S.Q. Zhou, D.M. (2009). Effects of low molecularweight organic acids on Cu(II) adsorption onto hydroxyapatite nanoparticles, *J. Hazard. Mater.* 162, 1135–1140.
- Wang, Y. Xing, Z. Li, Z. Wu, X. Wang, G. and Zhou, W. (2017). Facile synthesis of high thermostably ordered mesoporous TiO₂/SiO₂ nanocomposites: An effective bifunctional candidate for removing arsenic contaminations. *Journal of Colloid and Interface Science* 485, 32–38.
- Xu, T. Cai, Y. O'Shea, K.E. (2007). Adsorption and photo catalyzed oxidation of methylated arsenic species in TiO₂ suspensions, *Environ. Sci. Technol.* 41, 5471–5477.
- Yang, Z.P. Zhang, C.J. (2010). Kinetics of photocatalytic reduction of Pb(II) on nanocrystalline TiO₂ coatings: A quartz crystal microbalance study. *Thin Solid Films*, 518, 6006–6009.
- Yantasee, W. Rutledge, R.D. Chouyok, W. Sukwarotwat, V. Orr, G. Warner, C.L. Warner, M.G. Fryxell, G.E. Wiacek, R.J. Timchalk, C. Addleman, R.S. (2010). Functionalized nanoporous silica for the removal of heavy metals from biological systems: adsorption and application, *ACS Appl. Mater. Interfaces* 2, 2749–2758.
- Yazdani, M. Bhatnagar, A. and Vahala, R. (2017). Synthesis, characterization and exploitation of nano-TiO₂/feldsparembdedded chitosan beads towards UV-assisted adsorptive abatement of aqueous arsenic (As). *Chemical Engineering Journal* 316, 370–382.
- Yoon, S.H. Lee, S. Kim, T.H. Lee, M and Yu, S. (2011). Oxidation of methylated arsenic species by UV/S₂O₈²⁻. *Chemical Engineering Journal* 173, 290–295.
- Zhou, D.M. Wang, Y.J. Wang, H.W. Wang, S.Q. Cheng, J.M. (2010). Surface-modified nanoscale carbon black used as sorbents for Cu(II) and Cd(II), *J. Hazard. Mater.* 174, 34–39.
- Zhou, Q., Yang, N., Li Y., Ren B., Ding, X., Bian, H., Yao, X. (2020) Total concentration and sources of heavy metals pollution in global river and lake water bodies from 1972 to 2017, *Global Ecology and Conservation*, Vol. 22, e00925.